

**AMENDMENTS TO THE SPECIFICATION**

Please amend Table 3 on page 29 as follows:

Table 3

			Ex. 8	Ex. 9	Ex. 10	Comp. Ex. 7
Polyamide resin composition	Type of PA		PA6T /66	PA6T /66	PA6T /66	PA66 PA6T/66
	Amount of PA (part(s) by weight)		40	40	40	40
	Type and amount (part(s) by weight) of metallic soap	Li-Beh (22 carbon atoms)	0.2	0.4	-	-
		Mg-Beh (22 carbon atoms)	-	-	0.4	-
		Na-Mon (28 carbon atoms)	-	-	-	0.4
	Glass fiber (part(s) by weight)		30	30	30	30
	Flame retardant (part(s) by weight)		26	26	26	26
	Flame retarding assistant (part(s) by weight)		4	4	4	4
Evaluation item	Flame retardance		V-0	V-0	V-0	V-0
	HDT (°C)		296	295	295	295
	Flow length (mm)		73	75	76	65